

Technical Product Information

ROXUL CavityRock DD

BOARD INSULATION 07210* BOARD INSULATION 07 21 13** CAVITY WALL UNIT MASONRY 04 27 23**

General Product Information:

ROXUL® products are mineral wool fibre insulations made from basalt rock and slag. This combination results in a noncombustible product with a melting point of approximately 2150°F (1177°C), which gives it excellent fire resistance properties. ROXUL mineral wool is a water repellent yet vapour permeable material.

Description & Common Applications:

CavityRock® DD is a non-combustible, lightweight and water repellent, rigid insulation board with a rigid upper surface for durability and enhanced strength, intended for use in cavity wall applications. Specifically engineered for this application, CavityRock DD's low moisture sorption enables it to maintain R-value and its mineral fibre structure allows for effective drainage of water which penetrates the exterior wall. In addition, because CavityRock DD is a non-combustible insulation, installation of a fire stop is not required. The product is compatible with most air/vapour barrier systems, adhesives and wall ties.

Compliance and Performance:

CAN/ULC-S702 Mineral Fibre Thermal Insulation for Buildings Type 1, Complies
ASTM C 612 Mineral Fibre Block and Board Thermal Insulation Type IVB, Complies

Fire Performance:

ASTM E 136 Behaviour of Materials at 750°C (1382°F) Non-Combustible
CAN4 S114 Test for Non-Combustibility Non-Combustible
ASTM E 84(UL 723) Surface Burning Characteristics Flame Spread = 0

Smoke Developed = 0
CAN/ULC S102
Surface Burning Characteristics
Flame Spread = 0
Smoke Developed = 5

Water Vapour Permeance:

ASTM E 96 Water Vapour Transmission, Desiccant Method 1555 ng/Pa.s.m² (27.2 perm)

Moisture Resistance:

ASTM C 1104 Moisture Sorption 0.07%

Thermal Resistance:

ASTM C 518 (C 177) R-value/inch @ 75°F 4.3 hr.ft².F/Btu***
RSI value/25.4 mm @ 24°C 0.76 m²K/W

Fungi Resistance:

ASTM C 1338 Mold Growth Zero Growth

Corrosive Resistance:

ASTM C 665 Corrosiveness to Steel Pass
ASTM C 795 **** Stainless Steel Stress Corrosion Specification as per Test Conforms

Methods C871 and C692: U.S. Nuclear Regulatory Commission, Reg. Guide #1.36: U.S. Military Specifications

MIL-I-24244 (all versions including B and C)



Acoustical Performance

ASTM C423 CO-EFFICIENTS AT FREQUENCIES							
Thickness	125 Hz	250 Hz	500 Hz	1000 Hz	2000 Hz	4000 Hz	NRC
3.0"	0.72	0.93	0.88	0.84	0.90	0.97	0.90

Density:

ASTM C 612-00 – Actual
Outer Layer 6.2 lbs/ft³ 100 kg/m³
Inner Layer (2.5" board) 4.1 lbs/ft³ 65 kg/m³
Inner Layer (5.0" board) 3.4 lbs/ft³ 55 kg/m³

Dimensions:

16" (width) x 48" (length) 406 mm (width) x 1219 mm (length)

24" (width) x 48" (length) 610 mm (width) x 1219 mm (length)

Thickness:

Available in 2.5" to 5". Additional sizes available in $\frac{1}{2}$ " increments.

For additional sizes, please contact Roxul by phone at 1-800-265-6878.

Key Application Qualifiers:

- Non-combustible
- Low moisture sorption
- Non-corrosive
- Chemically inert
- Does not rot or sustain vermin
- Does not promote growth of fungi or mildew
- CFC and HCFC free product and process
- Made from natural & recycled materials

Other ROXUL Products:

Please consult ROXUL for all your insulation needs. We have an extensive range of products for all applications from pipe insulation to commercial products to residential batts. ROXUL invites all inquiries and will act promptly to service all of your requirements.

Note:

As ROXUL Inc. has no control over installation design and workmanship, accessory materials or application conditions, ROXUL Inc. does not warranty the performance or results of any installation containing ROXUL Inc's. products. ROXUL Inc's. overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty is in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose.

ROXUL INC. www.roxul.com Milton, Ontario Tel: 905-878-8474 Tel: 1-800-265-6878

Fax: 1-800-991-0110
Revised: November 24, 2010
Supersedes: December 11, 2009

Fax: 905-878-8077

^{**** &}quot;Provisions for lot testing may be required, consult manufacturer."