



W. R. MEADOWS.

SEALTIGHT

DATA SHEET NO. 3300-785

785 GENFLOR NON-METALLIC FLOOR HARDENER

DESCRIPTION

785 GENFLOR NON-METALLIC FLOOR HARDENER is a silica aggregate-based concrete hardener for use in commercial and industrial concrete floor applications. It will provide hard, durable floor surfaces. The product is available in natural or 20 standard colours.

USES

785 GENFLOR NON-METALLIC FLOOR HARDENER is used wherever concrete floor surfaces are to be subjected to medium or heavy usage and wherever colourful, abrasion-resistant floors and non-rusting floors are specified.

PACKAGING

25 Kg Multi-Wall Bag

COVERAGE

Normal Traffic: 27.5 - 35 kg/10 sq. m
(60 - 75 lb./100 sq. ft.)
Heavy Traffic: 34 - 46 kg/10 sq. m
(75 - 100 lb./100 sq. ft.)

NOTE: Coloured hardeners require 34-46 kg/10 sq. m (75-125 lb./100 sq. ft.) to achieve a uniform colour.

TECHNICAL DATA

Hardness 6.5 (Mohs Scale)
Particle Shape Rough, Angular

APPLICATION

Surface Preparation ... The concrete should be sufficiently set to support kneeboards and the surface water disappeared.

Application Method ... Broadcast 785 GENFLOR NON-METALLIC FLOOR HARDENER as it comes from the container, over the entire surface. Care should be taken to broadcast it low across the surface to prevent air currents from separating the material.

For uniformity of color and thickness, 785 GENFLOR NON-METALLIC FLOOR HARDENER should be applied in two shakes using approximately two-thirds of the total amount on the first shake and applying the second shake at right angles to the first. To achieve the most uniform color, the floor should not be overworked or worked when bleeding of the concrete is still evident. A colored shake must be worked in slowly, carefully and uniformly for proper distribution and depth of color.

Allow 785 GENFLOR NON-METALLIC FLOOR HARDENER to absorb moisture and float it into the surface with a wood float or mechanical trowel equipped with float blades in a flat position. **DO NOT** steel trowel. Apply second shake and again allow it to absorb moisture from the floor and then float into the concrete surface.

When the surface has become sufficiently firm, steel trowel to produce the desired finish. Cure the natural (non-colored) 785 GENFLOR NON-METALLIC FLOOR HARDENER concrete surface with SEAL CURE™ from W. R. MEADOWS.

Care must be taken when using floor hardener with concrete containing more than 3% entrained air, or containing high fly ash content. Contact a representative for recommendations.

2004 MASTERFORMAT NUMBER AND TITLE

03 35 00 – Concrete Finishing

W. R. MEADOWS OF WESTERN CANADA
38 Rayborn Crescent, St. Albert, AB T8N 5B4
Phone: (780) 458-8773 • Fax: (780) 458-1173

Hampshire, IL / Cartersville, GA / York, PA /
Fort Worth, TX / Benicia, CA / Pomona, CA
Goodyear, AZ / Milton, ON / St. Albert, AB
www.wrmeadows.com

LEED INFORMATION

May help contribute to LEED credits:

- IEQ Credit 4.3: Low-Emitting Materials – Flooring Systems
- MR Credit 4: Recycled Content
- MR Credit 5: Regional Materials

For most current data sheet, further LEED information and MSDS, visit www.wrmeadows.com.

2010-12-/07



© SEALTIGHT is a registered trade mark of W. R. Meadows

WARRANTY: W.R. MEADOWS of Western Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W.R. MEADOWS of Western Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W.R. MEADOWS of Western Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W.R. MEADOWS of Western Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.