



# PRODUCT DATA

CSI Code: 03 39 23



NO. 370

MAY 2008  
(Supersedes August 2006)

## 1100-CLEAR

Resin-Based, Water-Based Concrete Curing Compound

### DESCRIPTION

The 1100-CLEAR series of water-based concrete curing compounds is formulated from hydrocarbon resins and may be used on interior, exterior, vertical, and horizontal concrete surfaces. Once applied, 1100-CLEAR forms a premium-grade membrane that retains an optimum amount of water in freshly placed concrete for complete hydration of the cement. **NOTE:** After approximately four weeks, the membrane begins to chemically break down. The membrane will eventually dissipate from the surface. This process usually takes another 3 - 5 weeks under normal traffic, exposure to UV, and weathering conditions.

### USES

The 1100-CLEAR series has been used on both interior and exterior applications where paint, resilient tile or resilient flooring may be applied later. Because of the wide variety of coatings, paints, adhesives, and toppings available, contact the manufacturer of the flooring system or subsequent coating or topping for application approval over resin-based curing compounds. A small test application is always recommended.

### SPECIFICATIONS

- U.S. EPA Architectural Coatings Rule: 350 g/L maximum VOC for concrete curing compounds
- SCAQMD Rule 1113: 100 g/L maximum VOC for concrete curing compounds and waterproofing concrete/masonry sealers
- Ozone Transport Commission (OTC): 350 g/L maximum VOC for Concrete Curing Compounds
- ASTM C 309, Type 1, Classes A & B (Type 1-D also available)
- AASHTO M 148, Type 1, Classes A & B (Type 1-D also available)

### FEATURES/BENEFITS

- When properly applied, 1100-CLEAR produces a premium-grade film, which optimizes water retention.
- Furnished as a ready-to-use, true water-based compound.
- Produces hard, dense concrete ... minimizes hair checking, thermal cracking, dusting, and other defects.
- Offers a compressive strength significantly greater than improperly or uncured concrete.
- Increases tensile strength for greater resistance to cracking and surface crazing.
- Improves resistance to abrasion and the corrosive actions of salts and chemicals.
- Minimizes excessive shrinkage.
- Can be applied quickly and easily with conventional commercial spray equipment.
- Formulations are also available with red fugitive dye added.
- VOC compliant ... VOC content is <100 g/L.

### PACKAGING

5 Gallon (18.93 L) Pails  
55 Gallon (208.20 L) Drums

### TECHNICAL DATA

**Drying Time:** Typically dries in 1-2 hours, depending on jobsite conditions (temperature, wind, etc.) Restrict foot traffic for at least four hours; 12 hours is preferable.

**Flash Point:** >210° F (99° C).

*CONTINUED ON REVERSE SIDE...*

### W. R. MEADOWS, INC.

P.O. Box 338 • HAMPSHIRE, IL 60140-0338  
Phone: 847/214-2100 • Fax: 847/683-4544  
1-800-342-5976

[www.wrmeadows.com](http://www.wrmeadows.com)

HAMPSHIRE, IL / CARTERSVILLE, GA / YORK, PA  
FORT WORTH, TX / BENICIA, CA / POMONA, CA  
GOODYEAR, AZ / MILTON, ON / ST. ALBERT, AB

## LEED INFORMATION

May help contribute to LEED credits:

- EQ Credit 4.2: Low-Emitting Materials: Paints & Coatings
- MR Credit 5.1: Regional Materials: 10% Extracted, Processed & Manufactured Regionally
- MR Credit 5.2: Regional Materials: 20% Extracted, Processed & Manufactured Regionally

## APPLICATION

**Preparation ...** Application equipment must be clean and free of all previously used materials.

**Mixing ...** For optimum performance, gentle mixing or agitation is recommended. **CAUTION: TO AVOID FOAMING, DO NOT MIX EXCESSIVELY. DO NOT THIN.**

**Application Method ...** Apply in a uniform film to horizontal surfaces as soon as the surface water disappears and the surface will not be marred by walking workmen. On vertical surfaces, apply promptly after the forms are removed. 1100-CLEAR may be applied with a typical commercial hand or power sprayer. Use a Chapin 5797 or equivalent spray nozzle that produces a flow of 1/2 gal. (1.89 L) per minute under 40 psi (.276 MPa) of pressure.

**Coverage ...** Approximately 200 ft.<sup>2</sup>/gal. (4.91 m<sup>2</sup>/L). Coverage rate may vary depending on conditions (temperature, wind, etc.) at the jobsite, as well as the porosity and condition of the concrete.

**Cleanup ...** Prior to drying, cleanup can be accomplished with soap and water. Once dried, use mineral spirits or other suitable petroleum solvent.



## **LIMITED WARRANTY**

“W. R. MEADOWS, INC. warrants at the time and place we make shipment, our material will be of good quality and will conform with our published specifications in force on the date of acceptance of the order.” Read complete warranty. Copy furnished upon request.

## **Disclaimer**

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. W. R. MEADOWS, INC. cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As W. R. MEADOWS, INC. has no control over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.

## PRECAUTIONS

**KEEP FROM FREEZING.** Do not apply if air and/or concrete temperature is less than 40° F (4° C). Improper or over-application may increase the amount of time necessary for the film to dissipate from the surface. **SURFACE MAY DISCOLOR AND/OR YELLOW DUE TO OVER-APPLICATION. DO NOT MIX OR DILUTE WITH ANY OTHER PRODUCTS OR LIQUIDS.** Do not apply paint, resilient flooring or any other subsequent coatings or toppings without first checking the specifications and securing approval from the manufacturer of the product being applied over 1100-CLEAR. A small test application is always recommended. If removal of 1100-CLEAR is necessary, use **ULTRITE® DEGREASER** from W. R. MEADOWS.

## HEALTH AND SAFETY

Direct contact may result in mild irritation. Read and follow all application, precaution, label, and health and safety information prior to use. Refer to Material Safety Data Sheet for complete health and safety information.

## SHELF LIFE (TYPICAL)

One year in original, unopened container.

**FOR FURTHER LEED INFORMATION, MSDS, AND MOST CURRENT TECHNICAL DATA SHEET, VISIT [WWW.WRMEADOWS.COM](http://WWW.WRMEADOWS.COM).**