

## Typar® HouseWrap

### FOR RESIDENTIAL APPLICATIONS TYPICAL CHARACTERISTICS

Basis Weight	(ASTM D-5261)	nominal 2.8 osy 21.0 lbs/1000ft <sup>2</sup>
Thickness	(ASTM D-1777)	12.9 mils
Bursting Strength	(ASTM D-3786)	66 psi
Dry Tensile Strength	(ASTM D-5034)	80 lbs md 87 lbs xd
Trapezoidal Tear	(ASTM D-1117/ ASTM D-5733)	30 lbs md 33 lbs xd
Pliability	(AC-38)	PASS
Hydrostatic Pressure Resistance	(AATCC 127-1995)	865 cm
Gurley Hill Porosity	(TAPPI T-460)	> 2500 sec/100cc
Moisture Vapor Transmission Rate	(ASTM E-96-95, procedure A)	11.7 U.S. perms
Ultra Violet Light Exposure Resistance (UV)		6 months
“Air-Ins” (Air Leakage Test)	(CCMC Technical Guide MF-07273)	.0032L/(S·M <sup>2</sup> ) @ 75 pascals
Water Resistance Test (Boat Test)	(ASTM D-779)	PASS
Water Ponding Test	(CCMC Technical Guide MF-07193)	PASS
	(ASTM-E-84-00a)	
Surface Burning Characteristics		
Flame Spread Index		Class A
Smoke Developed Index		PASS

Roll sizes: 3 ft x 100 ft, 4.5 ft x 200 ft, 9 ft x 100 ft  
9.5 ft x 95 ft, 9 ft x 150 ft, 9 ft x 195 ft, 10 ft x 100 ft, 10 ft x 150 ft  
ICC #ESR-1404, CCMC #12892-R, CCMC #12894-R

The information contained herein is to the best of our knowledge accurate and reliable and is provided for the user’s assessment and verification. However, since the circumstances and conditions under which such information and the products discussed can be used may vary and are beyond our control, we make no warranty, expressed or implied, of merchantability, fitness or otherwise, or of the results to be obtained, or against patent infringement, and we disclaim all liability from any resulting damage or loss.

Typar®, Typar® Weather Protection System, and Typar® HouseWrap, are registered trademarks of Fiberweb, Inc.

Fiberweb, Inc., 70 Old Hickory Blvd., Old Hickory, TN 37138 USA, 1-800-284-2780 •  
Fax: 615-847-7068, www.typar.com